

IN THE CLAIMS

Please amend the claims as follows:

Please cancel claim 67.

1.-28. (Canceled)

29. (Currently Amended) A prosthetic knee joint comprising:

a first joint member comprising,

a first joint member bone fixation portion, said first joint member bone fixation portion being adapted to be securable to a bone, and

a first joint member load bearing and articulation portion,

a second joint member comprising,

a second joint member bone fixation portion, said second joint member bone fixation portion being adapted to be securable to a bone, and

a second joint member load bearing and articulation portion, the second joint member load bearing and articulation portion comprising a second joint member polycrystalline diamond compact having a substrate and a diamond table attached to the substrate, said second joint member polycrystalline diamond compact serving to form at least a portion of said second joint member load bearing and articulation portion, and wherein the diamond table forms a second joint member load bearing and articulation surface, said second joint member load bearing and articulation surface including diamond table comprising sintered polycrystalline diamond, said sintered polycrystalline diamond providing a smooth and low-friction second joint member load bearing and articulation surface.

30. (Previously Presented) A joint as recited in claim 29 further comprising solvent-catalyst metal located in said second joint member polycrystalline diamond compact.

31. (Withdrawn) A joint as recited in claim 29 wherein the joint further comprises a second joint member gradient transition zone between said second joint member polycrystalline diamond compact substrate and said second joint member polycrystalline diamond compact diamond table, and wherein said a second joint member gradient transition zone is located between said second joint member substrate and said second joint member diamond table, and wherein said second joint member gradient transition zone has a substrate side and a diamond table side, said second joint member gradient transition zone having both solvent-catalyst metal and diamond therein, and said second joint member gradient transition zone exhibiting a transition of ratios of percentage content of solvent-catalyst metal to diamond from one side of said gradient transition zone to another side such that at a first point in said second joint member gradient transition zone near said substrate side, the ratio of percentage content of solvent-catalyst metal to diamond is greater than it is at a second point in said second joint member gradient transition zone closer to said diamond side than said first point.

32. (Previously Presented) A joint as recited in claim 29 further comprising chemical bonds between said second joint member diamond table and said second joint member substrate which tend to secure said diamond table to said substrate.

33. (Previously Presented) A joint as recited in claim 29 further comprising a mechanical grip between said second joint member diamond table and said second joint member substrate which tends to secure said diamond table to said substrate.

34. (Previously Presented) A joint as recited in claim 33 further comprising topographical features on the second joint member substrate, said topographical features serving to enhance said mechanical grip between the substrate and its corresponding diamond table.

35. (Currently Amended) A joint as recited in claim 29 wherein said second joint member ~~load~~ bearing and articulation surface has a shape selected from the group consisting of concave, convex, arcuate, hemispherical and partially spherical.

36. (Currently Amended) A joint as recited in claim 29 further comprising a residual stress field in said polycrystalline diamond compact, said residual stress field tending to enhance strength of said polycrystalline diamond compact.

37. (Previously Presented) A joint as recited in claim 29 wherein the diamond in said polycrystalline diamond compact has a coefficient of thermal expansion CTE_{Cd} , and wherein said corresponding substrate has a coefficient of thermal expansion CTE_{sub} , and wherein CTE_{Cd} is not equal to CTE_{sub} .

38. (Currently Amended) A joint as recited in claim 29 wherein in said polycrystalline diamond compact, the diamond has a modulus $\underline{M_{Cd}}$ M_{Cd} , and the substrate has a modulus M_{sub} , and wherein M_{Cd} is not equal to M_{sub} .

39. (Currently Amended) A joint as recited in claim 29 wherein said second joint member load bearing and articulation surface has an Ra value of between about 0.01 to about 0.005 microns.

40. (Currently Amended) A joint as recited in claim 29 wherein said polycrystalline diamond load bearing articulation surface is burnished.

41. (Original) A joint as recited in claim 29 wherein at least one of said first and said second joint member bone fixation portions is shaped to be press fit into a receptacle formed in a bone.

42. (Original) A joint as recited in claim 29 wherein at least one of said first and said second joint member bone fixation portions includes a bone mating surface on at least a portion of its exterior.

43. (Original) A joint as recited in claim 29 wherein at least one of said first and said second joint member bone fixation portions includes a bone mating surface on at least a portion of the exterior that includes features which enhance frictional engagement with a bone.

44. (Previously Presented) A joint as recited in claim 29 wherein at least one of said first and said second joint member bone fixation portions includes a bone mating surface on at least a

portion of its exterior, said bone mating surface including a structure selected from the group consisting of metal mesh, porous metal, metal sintered beads, and plasma spray metal.

45. (Original) A joint as recited in claim 29 wherein at least one of said first and said second joint member bone fixation portions includes a bone mating surface on at least a portion of its exterior that includes a surface coating which encourages bone growth against said coating.

46. (Withdrawn) A joint as recited in claim 45 wherein said coating includes hydroxyl apatite.

47. (Withdrawn) A joint as recited in claim 29 wherein at least one of said first and said second joint member fixation portions is shaped to permit bone fixation to be accomplished by use of at least one mechanical fastener.

48. (Original) A joint as recited in claim 29 wherein said substrate includes at least one metal selected from the group consisting of cobalt, chrome, titanium, tungsten, molybdenum and iron.

49. (Previously Presented) A joint as recited in claim 29 wherein said substrate includes a material selected from the group consisting of cobalt chrome cemented tungsten carbide, cobalt chrome cemented chrome carbide, and metal cemented carbide.

50. (Original) A joint as recited in claim 29 wherein said substrate includes a plurality of substrate layers.

51. (Previously Presented) A joint as recited in claim 29 wherein said substrate includes at least two distinct substrate layers of different materials.

52. (Previously Presented) A joint as recited in claim 29 wherein said diamond table includes diamond crystals of at least two different sizes.

53. (Original) A joint as recited in claim 29 further comprising a first joint member load bearing and articulation surface, said first joint member load bearing and articulation surface including a counter bearing material against which said second joint member load bearing and articulation surface polycrystalline diamond may articulate.

54. (Withdrawn) A joint as recited in claim 53 wherein said counter bearing material includes a material selected from the group consisting of monocrystal diamond, natural diamond, polycrystalline diamond, CVD diamond, PVD diamond, cubic boron nitride, wurzitic boron nitride, ceramic, cobalt-chrome alloy, titanium alloy, nickel, vanadium, tantalum, hafnium, molybdenum, cemented tungsten carbide, niobium, zirconia ceramic, alumina ceramic, polymers, UHMWPE, PEEK, cross-linked polymers and sapphire.

55. (Currently Amended) A joint as recited in claim 29 wherein said first joint member load bearing and articulation portion comprises an articulation surface formed of a counter bearing material which is not as hard as said second joint member ~~load bearing and articulation surface~~.

56. (Currently Amended) A prosthetic knee joint comprising:

a first joint member comprising,
a first joint member bone fixation portion, said first joint member bone fixation portion being adapted to be securable to a bone, and
a first joint member load bearing and articulation portion,
a second joint member comprising,
a second joint member bone fixation portion, said second joint member bone fixation portion being adapted to be securable to a bone,
a second joint member load bearing and articulation portion, the second joint member load bearing and articulation portion comprising a load bearing and articulation surface located on said second joint member load bearing and articulation portion, and a ~~volume of~~ sintered polycrystalline diamond compact located on said load bearing and articulation portion, said ~~volume of~~ diamond compact material forming at least a portion of said load bearing and articulation surface.

57. (Currently Amended) A joint as recited in claim 56, wherein said ~~volume of~~ diamond compact comprises polycrystalline diamond and ~~wherein said second joint member load bearing and articulation portion comprises~~ a substrate to which said polycrystalline diamond is affixed.

58. (Currently Amended) A joint as recited in claim 57 further comprising a gradient transition zone between said polycrystalline diamond and said substrate.

59. (Original) A joint as recited in claim 58 further comprising chemical bonds between said polycrystalline diamond and said substrate.

60. (Original) A joint as recited in claim 59 further comprising a mechanical grip between said polycrystalline diamond and said substrate.

61. (Original) A joint as recited in claim 60 further comprising topographical features on said substrate, said topographical features serving to enhance said mechanical grip between said substrate and said polycrystalline diamond..

62. (Original) A joint as recited in claim 59 wherein said polycrystalline diamond and said substrate comprise a polycrystalline diamond compact.

63. (Original) A joint as recited in claim 62 further comprising a residual stress field in said polycrystalline diamond compact, said residual stress field tending to enhance strength of said polycrystalline diamond compact.

64. (Original) A joint as recited in claim 63 wherein said polycrystalline diamond has a coefficient of thermal expansion CTE_{Cd} , and said substrate has a coefficient of thermal expansion CTE_{sub} , and wherein CTE_{Cd} is not equal to CTE_{sub} .

65. (Currently Amended) A joint as recited in claim 63 wherein in said polycrystalline diamond has a modulus $\underline{M_{Cd}}$ M_{Cd} , and said substrate has a modulus M_{sub} , and wherein M_{Cd} , is not equal to M_{sub} .

66. (Original) A joint as recited in claim 56 wherein said diamond articulation surface has an Ra value of between about 0.5 to about 0.005 microns.

67.-100. (Canceled)